



## TECHNICAL DATASHEET

## Commercially Pure Titanium – Grade 3 FT 006 – Version 0

The four types of commercially pure titanium currently on the market (1/2/3/4) are used for applications requiring good ductility combined with excellent corrosion resistance, moderate strength and good weldability. The limited impurities are iron, oxygen and nitrogen, the variations in content of which define each grade's mechanical properties, from the softest and most ductile (Grade 1) through to the hardest and strongest (Grade 4).

Grade 3 titanium is the least used of the four CP titanium grades. Stronger than grades 1 and 2, its ductility is similar and its formability only slightly less.

APPLICATIONS	ADVANTAGES
Industrial Medical Aeronautic	Corrosion resistance Formability Weldability
STANDARDS	SHAPES
ASTM B348 / ASME SB348 ASTM B265 / ASME SB265 ASTM F67 ISO 5832-2 AMS 4900	Sheet / Plate Bar Grade not stocked, available on request

### ➤ CHEMICAL COMPOSITION

%	Fe	O	N	C	H	Other (each)	Other (total)	Ti
min								residue
max	0.3	0.35	0.05	0.08	0.015	0.1	0.4	

### ➤ MECHANICAL PROPERTIES

Rm Tensile strength (MPa)	Rp0.2 Yield strength (MPa)	Elongation (% min)	Necking (% min)
450	380	18	30

### ➤ PHYSICAL PROPERTIES

Density (g/cm <sup>3</sup> )	4.51
Hardness (HV)	180
Modulus of elasticity at 20°C (N/mm <sup>2</sup> )	105 x10 <sup>3</sup>
Thermal conductivity at 20°C (W/m °C)	19.9
Mean coefficient of thermal expansion at 20-200°C (mm °C)	9.1 x10 <sup>-6</sup>
Beta transus (°C)	921
Fusion temperature (°C)	1670